

TECHNICAL SPECIFICATION

Property	Reference Standard	Units	Nominal Value									
Basis Weight	ISO 536	g/m ²	120	160	180	210	240	315	370	490	640	
Taber Stiffness	MD	ISO 2493	mN.m	0.8	1.5	2.3	3.5	5.0	9.5	--	--	--
	CD			0.4	0.8	1.2	1.7	2.5	5.0	--	--	--
Thickness	ISO 534	μm	135	175	190	220	250	320	425	525	675	
Bekk Smoothness	ISO 5627	s	65	65	65	65	65	65	65	65	65	65
Moisture Content	ISO 287	%	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5
CIE Whiteness	ISO 11475	%	145.9	145.9	145.9	145.9	145.9	145.9	145.9	145.9	145.9	145.9

MD – Machine Direction; CD- Cross-Machine Direction


PRODUCT SPECIFICATION

Basis Weight (g/m ²)	Size (cm)	Packets per pallet	Reams per pallet	Sheets per pack	Finish
120	65X90	30	15	250	Glazed
160	By order				
180	50x65	80	20	125	
210	50x65	64	16	125	
240	50x65	60	15	125	
315	50x65	48	12	125	
370	50x65	40	10	125	
490	50x65	40	8	100	
640	50x65	60	6	50	

Mill certifications



Product certifications available



PEFC™ certified
This product is from sustainably managed forest and controlled sources.



By buying products with the FSC® label you are supporting the growth of responsible forest management worldwide.

www.papeldoprado.com